

台灣蠟品股份有限公司
TAIWAN WAX COMPANY, LTD.

WAX-135
CERTIFICATE OF ANALYSIS

Analysis Item (分析項目)	135F1110-22	135F0831-22	135F0706-22	135F0422-22	135F0301-22	Specification (規格)	Test Method (測試方法)
Specific Gravity at 100°C (比重)	0.766	0.765	0.766	0.765	0.765	0.76—0.77	ASTM D1298
Melting Point, °F (熔點)	134.6	133.9	135.1	134.0	134.0	132—136	ASTM D 87
Needle Penetration, (針入度) mm/10 77°F	16.5	16.0	15.0	15.0	14.5	11.0—17.0	ASTM D1321
Kinematic Viscosity, (動黏度) cSt. at 212°F cSt. at 275°F	3.715 2.438	3.845 2.554	3.914 2.555	3.816 2.496	3.802 2.467	3.4—4.0 as report	ASTM D445
Oil Content, wt% (油含量)	0.385	0.383	0.358	0.369	0.372	Max. 0.5	ASTM D721
Saybolt Color (色度)	+30	+30	+30	+30	+30	+26—+30	ASTM D156
Flash Point, °C (閃火點)	225	224	225	224	224	Min. 220	ASTM D92
Conclusion (結論)							

Remark (備註):

1. Please keep the product away from open flames, hot surfaces, sources of ignition, and direct sunlight.
2. Unit conversions: °C = (°F - 32) / 1.8 ; °F = (°C × 1.8) + 32.