

## Dipentaerythritol 雙異戊四醇(90% grade)

<b>Features 特性:</b> <ul style="list-style-type: none"> <li>• 白色粉末 white powder</li> <li>• 微溶於水 slightly soluble in water</li> </ul>	<b>Typical Application 一般應用:</b> <table style="width: 100%; border: none;"> <tr> <td style="padding-right: 20px;">抗 UV 樹脂</td> <td>Anti-UV resins</td> </tr> <tr> <td>塑化安定劑</td> <td>Plastics Stabilizer</td> </tr> <tr> <td>潤滑油</td> <td>Lubricating oils</td> </tr> <tr> <td>抗氧化劑</td> <td>Anti-Oxidants</td> </tr> <tr> <td>炸藥</td> <td>Explosives</td> </tr> <tr> <td>油墨</td> <td>Inks</td> </tr> </table>			抗 UV 樹脂	Anti-UV resins	塑化安定劑	Plastics Stabilizer	潤滑油	Lubricating oils	抗氧化劑	Anti-Oxidants	炸藥	Explosives	油墨	Inks
抗 UV 樹脂	Anti-UV resins														
塑化安定劑	Plastics Stabilizer														
潤滑油	Lubricating oils														
抗氧化劑	Anti-Oxidants														
炸藥	Explosives														
油墨	Inks														
<b>Typical Properties</b>	<b>Test Method</b>	<b>Unit</b>	<b>Value</b>												
一般性質	測試方法	單位	數值												
Purity 純度	ASTMD 2195-89	wt%	90 min												
Hydroxyl 氫氧基	ASTMD 2195-89	wt%	38 min												
Moisture 水份	ASTMD 2195-89	wt%	0.2 max												
Ash 灰份	ASTMD 2195-89	wt%	0.05 max												
Melting point 熔點	ASTMD 2195-89	°C	218 min												
Color 色度	ASTMD 2195-89	Gardner	3 max												