

台灣品股份有限公司
125°F 成品蠟分析報告

Date	1121016	1120710	1120420	1111215	1110913	1110620	1110215	1101116	1100714	1100308
ASTM D1298 Specific Gravity 100°C	0.760	0.761	0.761	0.760	0.761	0.761	0.760	0.760	0.761	0.760
ASTM D87 Melting Point °F	126.9	127.3	127.2	127.0	127.6	127.9	127.5	127.2	127.7	127.4
ASTM D1321 Needle Penetration mm/10;25°C	20.5	20	20	20	19	19	19.5	20	19	19.5
ASTM D445 Kinematic Viscosity cst 100°C	3.366	3.372	3.370	3.368	3.409	3.411	3.401	3.376	3.413	3.392
ASTN D721 Oil Content wt%	0.523	0.502	0.512	0.519	0.502	0.495	0.505	0.514	0.491	0.519
ASTM D156 Saybolt Color	+30	+30	+30	+30	+30	+30	+30	+30	+30	+30
ASTM D92 Flash Point(c.o.c) °C	212	214	213	212	214	214	213	212	213	212