



# Nan Ya Plastics Corporation

Petrochemicals 2<sup>nd</sup> Division

201 Tung Hwa N. Road, Taipei, Taiwan, R.O.C

Tel. : 886-2-2712-2211 ext. 5811

Fax. : 886-2-2719-8661

e-mail : philiphs@npc.com.tw

## Bisphenol-A PC Grade Specification Sheet (Prill)

Properties	Unit	Specification	Analysis Method
Appearance	-----	white bead	visual inspection
Purity	wt %	99.8 min.	ASTM E682
Free Phenol Content	ppm	100 max.	
O,P-BPA Content	ppm	500 max.	
Moisture Content	ppm	1000 max.	ASTM D1364
Molten Color	APHA	25 max.	JIS K4101
Melting Point	°C	156.5 min.	
Ash Content	ppm	20 max.	
Iron Content	ppm	1 max.	JIS K0102