

取樣點		Solid MA	Solid MA	Solid MA	Solid MA	Solid MA	Solid MA	Solid MA	Solid MA	Solid MA
註冊日期		2012/6/7	2012/6/21	2012/7/5	2012/7/19	2012/8/2	2012/8/16	2012/8/31	2012/9/13	2012/9/27
MA	wt%	99.79	99.71	99.86	99.86	99.84	99.79	99.81	99.83	99.85
Appearance briquettes		Briquettes	Briquettes	Briquettes	Briquettes	Briquettes	Briquettes	Briquettes	Briquettes	Briquettes
Color	APHA	20	20	20	20	20	20	20	20	20
Heat Stability 180oC*20 min	APHA	35	30	30	30	30	35	30	35	30