




产 品 说 明 书

产品信息

产品名称: 氢化双酚 A
 产品品牌: 惠成 HC
 产品编号: C0046
 CAS 号: 80-04-6
 分子式: $C_{15}H_{28}O_2$
 分子量: 240.38

分子结构:



技术指标

项 目	指 标
外观	白色固体
色度(30%甲醇溶液)(Pt-Co),Hazen	≤30
羟值, mg KOH/g	≥435
含量, %	≥95.0
水分, %	≤0.5

用 途

氢化双酚 A 主要用于制造环氧树脂、聚碳酸酯、聚丙烯酸树脂、不饱和树脂等, 具有热稳定性、化学稳定性及耐候性, 电性能优良、粘度低、加工工艺性好等优点。氢化双酚 A 型环氧树脂作为耐候型环氧树脂, 解决了普通双酚 A 型环氧树脂固化物耐候性较差, 在室外易老化、风化等应用上的限制问题。



HUICHENG
惠成

濮阳惠成电子材料股份有限公司
Puyang Huicheng Electronic Material Co., Ltd
网 址: www.huichengchem.com.cn

包 装

20Kg/袋

储 存

本品储存过程中应避光、密闭、防潮，远离火源。



HUICHENG
惠成

网 站Web: www.huichengchem.com
邮 箱Email: services@huichengchem.com
地 址Add: 中国 河南 濮阳市胜利西路30号

电 话Tel: +86 393-8917710
传 真Fax: +86 393-8912775
邮 编zip: 457000



HUICHENG
惠成


濮阳惠成电子材料股份有限公司
Puyang Huicheng Electronic Material Co., Ltd
Website: www.huichengchem.com

Product Specification

Basic information

Product Name: 4,4'-Isopropylidenedicyclohexanol
Synonyms: HBPA
Product Brand: HC
Product No.: C0046
CAS No.: 80-04-6
Molecular Formula: C₁₅H₂₈O₂
Molecular Weight: 240.38

Chemical Structure:



Technical Data

Items	Index
Appearance	White solid
Color (30% methanol solution)(Pt-Co),Hazen	≤30
Hydroxyl value; mg KOH/g	≥435
Purity, %	≥95.0
Water content, %	≤0.5

Application

HBPA is mainly used in the manufacture of epoxy resin, polycarbonate, acrylic resin, unsaturated resin, with characteristics of thermal stability, chemical stability and weather resistance. Furthermore, HBPA has excellent electrical performance, low viscosity and good



Web: www.huichengchem.com
Email: services@huichengchem.com
Add: 30 West Shengli Road, Puyang, China

Tel: +86 393-8917710
Fax: +86 393-8912775
Zip: 457001



HUICHENG
惠成

濮阳惠成电子材料股份有限公司
Puyang Huicheng Electronic Material Co., Ltd
Website: www.huichengchem.com

processing usability etc. Compare to bisphenol A type epoxy resin, HBPA type epoxy resin can solve the application limitation of poor weather resistance, easy to aging and air-slake.

Package	20Kg/bag
Storage	This product shall be airtight, out of the sun, moisture-proof and away from heat .The storage period is one year.



Web: www.huichengchem.com

Email: services@huichengchem.com

Add.: 30 West Shengli Road, Puyang, China

Tel: +86 393-8917710

Fax: +86 393-8912775

Zip: 457001