

NITROCELLULOSE 硝化纤维素

Wetting agent (湿润剂): Ethanol; IPA; NBA; Water

- 1、Appearance (外观): white wool (白色絮状)
- 2、Heat resistant test (耐热度): ≥ 10 min
- 3、Explosive point(爆发点): $\geq 180^{\circ}\text{C}$
- 4、Moisture content(水分%): clear in mixed solvent(在混合溶剂中不显浑浊)
- 5、Other performance indicators 其他性能指标:

规格 Specification	粘度 Viscosity	酸度 Acidity%	含氮量 Nitrogen%	湿润剂 Damping media%	透光率 Transmitting rate%	灰分 Ash content%
	1/8	1.7-3.0	≤ 0.08			
L	1/4a	3.1-6.5				
	1/4b	6.6-10.0	≤ 0.07	10.7-11.4	33 \pm 2	
	1/2a	3.2-6.0				
	1/2b	6.1-8.4	≤ 0.06			
H	1/16	1.0-1.6				
	1/8	1.7-3.0	≤ 0.08		≥ 85	≤ 0.2
	1/4a	3.1-4.9				
	1/4b	5.0-8.0	≤ 0.07			
	1/4c	8.1-10.0				
	1/2a	3.2-6.0				
	1/2b	6.1-8.4		11.5-12.2	30 \pm 2	
	1	8.5-16.0				
	3	2.0-4.0				
	10	5.0-12.0	≤ 0.06			
15	13-20					
30	21-40					
60	41-80					
120	81-160					

